



TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org

Results of Tests on Brick conducted in accordance with ASTM C67-14 Standard Method for Sampling and Testing

Brick and Structural Clay Tile

12/11/2016

Name:	The Belden Brick Company 700 West Tuscarawas Street Canton , OH 44702	Plant:	The Belden Brick Company	*Temperature: 60 - 90F
Phone:	330-456-0031	Report Number:	7284-15683	*Humidity: 30% - 70%
Fax:	330-456-2694	Received Date:	11/16/2016	
		Sampled Date:	11/16/2016	
		Lot:	03-16-21	
		Product Code:	03750P02014A0B3	

Sample Description: **PLT 3, Fireclay, No Additive (Face)**

						Average	Test Date
Absorption	1	2	3	4	5		
24 Hour Submersion in Cold Water (%)	3.98	4.58	4.78	4.98	4.21	4.51	11/18/2016
5 Hour Submersion in Boiling Water (%)	7.97	8.38	9.01	8.91	8.26	8.50	
Saturation Coefficient (Ratio of 24H to 5H)	0.50	0.55	0.53	0.56	0.51	0.53	
Compressive Strength	1	2	3	4	5	Average	
<i>psi</i>	9,783	8,754	7,901	6,990	11,741	9,034	11/18/2016
<i>MPa</i>	67.5	60.4	54.5	48.2	81.0	62.3	
IRA (Oven Dried Method)	6	7	8	9	10	Average	
<i>g/min/30 in.²</i>	16.4	18.0	28.1	16.3	18.6	19.5	11/18/2016
Abrasion Resistance	1	2	3	4	5	Average	
	0.04	0.05	0.06	0.07	0.04	0.05	11/18/2016

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 216 - 16 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)
Grade: SW, MW

ASTM C 902 - 15 Standard Specification for Pedestrian and Light Traffic Paving Brick
Class: SX, MX, NX

Type: I, II, III

Michael Walker, Quality Manager

**The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH
The results shown above apply only to the samples tested, which are provided by the customer.
This test report shall not be reproduced except in full, without written approval of the laboratory.*