





*Temperature: 60 - 90F

*Humidity: 30% - 70%

TEST REPORT

100 Clemson Research Blvd. Anderson, SC 29625 (864) 656-1094 Fax: (864) 656-1095 www.brickandtile.org

Results of Tests on Brick conducted in accordance with ASTM C67-14 Standard Method for Sampling and Testing

Brick and Structural Clay Tile

12/08/2016

The Belden Brick Company Name:

P. O. Box 430

Sugarcreek, OH 44681

Phone: 330-852-2424

Fax:

330-852-2958

Plant: The Belden Brick

Company

7212-15393 Report Number:

10/12/2016

Received Date: Sampled Date:

10/12/2016

Lot:

Product Code:

Sample Description: PLT 6, All Shale, No Additive

							Test Date
Absorption	1	2	3	4	5	Average	
24 Hour Submersion in Cold Water (%)	3.43	2.77	2.85	2.83	2.68	2.91	10/14/2016
5 Hour Submersion in Boiling Water (%)	4.74	4.22	4.63	4.25	4.89	4.55	
Saturation Coefficient (Ratio of 24H to 5H)	0.72	0.66	0.61	0.67	0.55	0.64	
Compressive Strength	1	2	3	4	5	Average	
psi	16,104	15,936	15,344	16,280	17,028	16,138	10/14/2016
MPa	111.0	109.9	105.8	112.2	117.4	111.3	
Efflorescence	11	12	13	14	15		
	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		10/24/2016
IRA (Oven Dried Method)	6	7	8	9	10	Average	
g/min/30 in.²	6.1	6.8	5.7	6.1	5.9	6.1	10/19/2016
Average % Void	20.0						10/18/2016
Abrasion Resistance	1	2	3	4	5	Average	
	0.02	0.02	0.02	0.02	0.02	0.02	10/18/2016

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 216 - 16 Standard Specification for Facing Brick (Solid Masonry Units Made From Clay or Shale)

Grade: SW, MW

ASTM C 902 - 15 Standard Specification for Pedestrian and Light Traffic Paving Brick

Class: SX, MX, NX

Type: I, II, III

Michael Walker, Quality Manager

Lab Reference: 7212.15393 Page 1 of 1